

Kinkaid Stone Company Aggregate Gradations

Grad No.

Sieve Size and Percent Passing

Fine Aggregate

	3/8	No.4	No. 8	No.10	No.16	No.30	No.40	No.50	No.80	No.100	No.200
FA-20	100	97 ± 3	80 ± 20		50 ± 15			19 ± 11		10 ± 7	4 ± 4
FA-21	100	97 ± 3	80 ± 20		57 ± 18			30 ± 10		20 ± 10	9 ± 9

AG Lime

Normal

For Gradation and CCE, MG values plus Correction Factors see Illinois Voluntary Limestone Program Producer Information

[\(Link\)](#)